

TITLE COAT WEIGHT OF FORMULATIONS #1-6 B ok No. 24  
FROM PP143-149

153

From Pag No. \_\_\_\_\_

| #    | Formulation                   | Coat weight plus<br>1 mil PET | * 0.0315g PET<br>- 1 mil PET | COAT WEIGHT / 10 CM <sup>2</sup>                |
|------|-------------------------------|-------------------------------|------------------------------|---|
| P143 | 1 1430 / 1.2 PD / 15 Sel FB   | 0.1392g                       | 0.1077                       | $\bar{X} = 113.6 \text{ Mg} \pm 6.27 (5.5\%)$   |
|      | " " "                         | 0.1517                        | 0.1202                       |   |
|      | " " "                         | 0.1445                        | 0.1130                       |   |
| P143 | 2 1430 / 1.2 PD / 15 Sel FB   | 0.1647                        | 0.1332                       | $\bar{X} = 133.17 \text{ Mg} \pm 0.75 (0.56\%)$ |
|      | " " "                         | 0.1639                        | 0.1324                       |   |
|      | " " "                         | 0.1654                        | 0.1339                       |   |
| P144 | 3 1753 / 15 Sel FB            | 0.1612                        | 0.1297                       | $\bar{X} = 129.97 \text{ Mg} \pm 0.38 (0.29\%)$ |
|      | " " "                         | 0.1613                        | 0.1298                       |   |
|      | " " "                         | 0.1619                        | 0.1304                       |   |
| P144 | 4 1753 / 1.2 PD / 15 Sel FB   | 0.1863                        | 0.1548                       | $\bar{X} = 156.13 \text{ Mg} \pm 1.89 (1.2\%)$  |
|      | " " "                         | 0.1898                        | 0.1583                       |   |
|      | " " "                         | 0.1868                        | 0.1553                       |   |
| P147 | 5 1430 / 1.2 PD / 11.3 Sel FB | 0.1833                        | 0.1518                       | $\bar{X} = 148.97 \text{ Mg} \pm 4.23 (2.8\%)$  |
|      | " " "                         | 0.1825                        | 0.1510                       |   |
|      | " " "                         | 0.1756                        | 0.1441                       |   |
| P147 | 6 1753 / 1.2 PD / 11.3 Sel FB | 0.1458                        | 0.1143                       | $\bar{X} = 114.4 \text{ Mg} \pm 0.36 (0.32\%)$  |
|      | " " "                         | 0.1456                        | 0.1141                       |   |
|      | " " "                         | 0.1463                        | 0.1148                       |   |

\* 1.0 mil PET 0.0315g on P69 this notebook

T Pag No. \_\_\_\_\_

Witnessed & Understood by me,

*[Signature]*

Date

Initiated by

Date

Recorded by

*[Signature]*